







Reference Figure 1

		Example 1	Comparative Example 2
Weight	$\text{g/m}^2$	70	71
Thickness	$\mu\text{m}$	96	87
Air permeability	$\text{cc/cm}^2/\text{sec}$	3.4	5.0
Pore size Average value	$\mu\text{m}$	10.1	12.1
Tensile strength ratio Longitudinal/Transverse		1.3/1	4.4/1
Diameter of the curled paper (after cast)	$\text{mm}\Phi$	 27 $\text{mm}\Phi$	 17 $\text{mm}\Phi$
Load for curl control (sample size 10 cm X 15 cm)	g	 4.88 g	 11.81 g